CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 07/06/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 07/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	151.77 X 149.80 X 151.56	22735	8.586	616.8	27.1	27.6
2	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	150.02 X 150.67 X 149.48	22604	8.206	603.4	26.7	
3	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	151.18 X 149.26 X 151.54	22565	8.245	654.1	29.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕಕಾರ್ಯಪಾಲಕಅಭಿಯಂತರರು
ಬೃಹತ್ ಮಳೆ ನೀರುಗಾಲುವೆ ಉಪ-ವಿಭಾಗ,
ದಾಸರಹಳ್ಳಿ ವಲಯ, ಬಿ.ಬಿ.ಎಮ್.ಪಿ. ಬೆಂಗಳೂರು

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 17/05/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	17/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	10/05/2019	17/05/2019	151.87 X 149.47 X 150.38	22700	8.572	529.5	23.3	23.1
2	Drain Bottom Raft Concrete	M25	10/05/2019	17/05/2019	151.82 X 150.10 X 150.27	22788	8.136	524.0	23.0	
3	Drain Bottom Raft Concrete	M25	10/05/2019	17/05/2019	150.73 X 149.07 X 149.88	22470	8.791	516.0	23.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 07/06/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	07/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	150.30 X 150.56 X 150.20	22629	8.586	622.2	27.5	27.3
2	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	151.69 X 151.32 X 151.77	22953	8.206	599.5	26.1	
3	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	151.34 X 149.53 X 149.58	22629	8.245	642.9	28.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-01-31-86** **Date: 17/05/2019**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	17/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	10/05/2019	17/05/2019	149.15 X 150.75 X 151.79	22485	8.572	527.8	23.5	22.9
2	Drain Bottom Raft Concrete	M25	10/05/2019	17/05/2019	151.73 X 150.06 X 150.90	22768	8.136	511.1	22.4	
3	Drain Bottom Raft Concrete	M25	10/05/2019	17/05/2019	150.51 X 150.72 X 150.28	22684	8.791	519.1	22.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-01-31-86** **Date: 07/06/2019**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	07/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	149.11 X 149.98 X 151.41	22363	8.586	620.8	27.8	27.4
2	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	150.60 X 151.97 X 150.26	22887	8.206	604.1	26.4	
3	Drain Bottom Raft Concrete	M25	10/05/2019	07/06/2019	150.18 X 151.74 X 149.56	22789	8.245	641.7	28.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕಕಾರ್ಯಪಾಲಕಅಭಿಯಂತರರು
ಬೃಹತ್ ಮಳೆ ನೀರುಗಾಲುವೆ ಉಪ-ವಿಭಾಗ,
ದಾಸರಹಳ್ಳಿ ವಲಯ, ಬಿ.ಬಿ.ಎಮ್.ಪಿ. ಬೆಂಗಳೂರು

Page 1/1
****End of Report****

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 24/05/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	24/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	151.71 X 150.91 X 150.78	22894	8.572	537.9	23.5	23.0
2	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	151.63 X 149.71 X 149.29	22701	8.136	522.1	23.0	
3	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	149.54 X 151.68 X 149.08	22683	8.791	510.4	22.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2020-01-31-86 **Date: 14/06/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-05-19

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	151.88 X 151.69 X 151.39	23039	8.586	635.0	27.6	27.4
2	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	150.49 X 149.11 X 150.70	22440	8.206	591.6	26.4	
3	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	150.33 X 151.56 X 149.28	22783	8.245	646.2	28.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕಕಾರ್ಯಪಾಲಕಅಭಿಯಂತರರು
ಬೃಹತ್ ಮಳೆ ನೀರುಗಾಲುವೆ ಉಪವಿಭಾಗ
ದಾಸರಹಳ್ಳಿ ವಲಯ, ಬಿ.ಬಿ.ಎಂ.ಪಿ.

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 24/05/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	24/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	151.04 X 151.63 X 149.40	22902	8.572	537.5	23.5	22.9
2	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	151.95 X 150.58 X 151.49	22882	8.136	517.4	22.6	
3	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	151.99 X 149.69 X 149.03	22751	8.791	513.6	22.6	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 14/06/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	14/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	150.45 X 150.29 X 149.12	22612	8.586	621.0	27.5	27.6
2	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	151.33 X 150.53 X 149.15	22780	8.206	611.8	26.9	
3	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	149.91 X 150.37 X 150.38	22542	8.245	639.1	28.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No. : TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 24/05/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K Jayamma, #H No:74, Behind Grama Panchayat Office, Sgnbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	24/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	149.64 X 151.32 X 150.91	22644	8.572	537.3	23.7	22.8
2	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	149.16 X 150.58 X 151.87	22460	8.136	507.3	22.6	
3	Drain Bottom Raft Concrete	M25	17/05/2019	24/05/2019	151.86 X 149.10 X 151.74	22642	8.791	500.7	22.1	

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-31-86**

Date: 14/06/2019

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-05-19

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	150.17 X 151.28 X 149.57	22718	8.586	623.3	27.4	27.5
2	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	150.57 X 150.29 X 150.96	22629	8.206	598.6	26.5	
3	Drain Bottom Raft Concrete	M25	17/05/2019	14/06/2019	150.43 X 149.80 X 150.69	22535	8.245	642.3	28.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-31-86** **Date: 24/05/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18.

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-05-19

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 24/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	17/05/2019	24/05/2019	151.81 X 150.53 X 151.34	22852	8.572	547.3	24.0	23.1
2	Drain Side Wall Concrete	M25	17/05/2019	24/05/2019	150.26 X 151.34 X 150.90	22741	8.136	519.0	22.8	
3	Drain Side Wall Concrete	M25	17/05/2019	24/05/2019	151.94 X 151.65 X 151.72	23041	8.791	518.3	22.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕಕಾರ್ಯಪಾಲಅಭಿಯಂತರರು
ಬೃಹತ್ ಮಳೆ ನೀರುಗಾಲುವೆ ಉಪ-ವಿಭಾಗ,
ದಾಸರಹಳ್ಳಿ ವಲಯ, ಬಿ.ಬಿ.ಎಮ್.ಪಿ. ಬೆಂಗಳೂರು

FOR CIVIL Pro.
R KARTHIIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner